

EGOSHANTUNG



Decorative interior paint for a Shantung silk effect. The finish, with a pleasant tactile and visual effect, reproduces the effect of the precious silk cloth, characterized by a rough, uneven and rough-looking surface.

Colour: Colour chart

Bases S.S.C.: Mother of pearl - gold - copper

Packaging: 0.750 - 2.5 litres

Product characteristics

Composition: Based on acrylic resin in aqueous dispersion and special Mica pigments.

Mean specific weight: 1.000 kg/l.

Drying time: 3 - 8 hours as a function of the thickness applied.

Spreading rate: 6 - 8 sqm/liter

Coverage: Excellent.

Filling: Excellent.

Film Aspect: Semi-opaque.

Adhesion: Excellent.

Storage: In tightly sealed cans, protected from frost.

Instructions for use

Use: To decorate plaster, plasterboard, properly prepared.

Application method: Plastic spatula and brush Fractal.

Dilution: Ready to use.

Application temperature range: 8 - 30 °C.

Cleaning of equipment: Clean with water immediately after use.

Systems of application

Old or new Plaster

- Surfaces must be dry and mature.
- Sand thoroughly, removing any old coats of loose paint.
- Apply one brush coat of Isolante Acrilico, diluted 400% by volume with water.
- Apply one roller coat of Super Quarzolin Sigillo Oro of the same finishing color, diluted 40% in volume with water. For slightly covering colors provide a second coat.
- Apply a spatula-coat of undiluted Egoshantung, creating vertical bands. When the product is still wet, brush with brush-fractal from bottom to top and vice versa in order to align the finish.

Considering the particularity of the product, when using multiple packages it is recommended that the required amount of the product is mixed in a single container. We recommend the application of the product according to the techniques described above. We also recommend the presence of two people so as to speed up and even the texture of the surface.

Product specification

Decorative interior paint for a Shantung silk effect (type: Egoshantung). The finish, with a pleasant tactile and visual effect, reproduces the effect of the precious silk cloth, characterized by a rough, uneven and rough-looking surface.

Mean specific weight: 1.000 kg/l.

Drying time: 3 - 8 hours as a function of the thickness applied.

Spreading rate: 6 - 8 sqm/liter

Coverage: Excellent.

Filling: Excellent.

Film Aspect: Semi-opaque.

All technical information contained herein is indicative.

For more detailed information, please consult our TECHNICAL SERVICE DEPARTMENT.